

TS-400

70-63

Metaflux®

Technical Data Sheet

DESCRIPTION:

Prevents formation of rust on steel and stops corrosion on surfaces that are already affected by rust. We recommend conducting a compatibility test prior to application on systems using high percentages of solvents.

USE DIRECTIVES:

Shake well before use.

Do not expose to temperatures exceeding 50 °C/122 °F. Keep away from heat/sparks/open flames/hot surfaces. No smoking. Do not spray on an open flame or other ignition source. Do not pierce or burn, even after use. Use only outdoors or in a well-ventilated area. Wash hands/nails/face thoroughly after handling. Wear gloves/protective clothing/eye protection/face protection. Before handling, it is very important that engineering controls are operating, and that protective equipment requirements and personal hygiene measures are being followed. People working with this chemical should be properly trained regarding its hazards and its safe use. Inspect containers for leaks before handling. Label containers appropriately. Ensure proper ventilation. Avoid breathing dust/fume/gas/mist/vapours/spray. Avoid contact with eyes, skin and clothing. Keep away from heat, sparks and flame. Avoid generating high concentrations of dusts, vapours or mists. Keep away from incompatible materials. Keep containers closed when not in use. Empty containers are always dangerous.

PROPERTIES AND ADVANTAGES:

- Density: 1.41 g / ml
- Storage: in closed packaging: 1 year
- Solids content: 62.10%
- Viscosity: 280 mPas
- Operating temperatures: 4 - 40 ° C
- Drying: approx. 3 hours, let dry 24 hours before painting
- Resistance of dry film to temperatures: P + 140 ° C / P - 40 ° C
- Yield: 1 kg for 5 to 7 m²
- Primary corrosion protection for all metals.
- Fast drying.
- Effective and durable protection.
- Can be diluted.
- Adheres perfectly to bare and clean metals.
- Can be covered with all usual paints and varnishes (for paint systems with a high solvent content, test compatibility beforehand)
- Meets the requirements of spot welding.
- Offers good stability to U.V.
- Operating temperature: 4 to 40 ° C; optimum temperature: 15-28 ° C
- Storage temperature from 4 to 40 ° C; protect from frost.
- Very good results of salt spray tests.



Content	Type	Art.-No	Box
1kg.	vrac grey	70-6300	12
5kg.	vrac grey	70-6305	2
5kg.	vrac black	70-3801	2
1L.	thinner	70-6301	12

1392, Avenue de la gare Mascouche (QC) Canada, J7K 2Z2

1-(888) 452-6382 (450) 477-3102 1-(450) 477-6664

www.ametasolution.com info@ametasolution.com



AMETA
SOLUTION.COM