

ZINC COMBI SPRAY

79-01

Metaflux®

Technical Data Sheet

DESCRIPTION:

Surface treatment product. Bright Zinc: combined protection based on zinc, aluminum and resins for all clean metal surfaces. Protective coating with high quality gloss finish for all agricultural and commercial metal constructions, gutters, fences, and truck platforms, trailers, doors, telephone booths, kiosks, etc.

USE DIRECTIVES:

Remove oil, grease and impurities from the surfaces to be treated with the [70-15 quick cleaning spray](#). Shake the aerosol well before use. Spray in thin, even, crossed layers from a distance of about 25cm. Flammable. Observe the advice mentioned on the aerosol.

Protect from sunlight. Do not expose to temperatures exceeding 50 °C/122 °F. Keep away from heat/sparks/open flames/hot surfaces. No smoking. Do not spray on an open flame or other ignition source. Do not pierce or burn, even after use. Use only outdoors or in a well-ventilated area. Wash hands/nails/face thoroughly after handling. Wear gloves/protective clothing/eye protection/face protection. Before handling, it is very important that engineering controls are operating, and that protective equipment requirements and personal hygiene measures are being followed. People working with this chemical should be properly trained regarding its hazards and its safe use. Inspect containers for leaks before handling. Label containers appropriately. Ensure proper ventilation. Avoid breathing dust/fume/gas/mist/vapours/spray. Avoid contact with eyes, skin and clothing. Keep away from heat, sparks and flame. Avoid generating high concentrations of dusts, vapours or mists. Keep away from incompatible materials. Keep containers closed when not in use. Empty containers are always dangerous.

PROPERTIES AND ADVANTAGES:

- Glossy hot-dip galvanized finish
- Color gray-silver
- Zinc in dry sheet 79% (+/- 1%)
- Zinc purity 98.5 - 99%
- High metallic content.
- Facilitates welding and tacking operations.
- Fast drying.
- Spray in all positions, even upside down,
- The appearance of the deposited layer is identical to hot-dip galvanizing.
- Complies with the new standard • Euro-Din • ISO en 1461 for touch-ups defects on parts under approval.
- The treated surface changes over time in the same way as a galvanized part.



Content	Type	Art.-No	Box
400ML	AEROSOL	79-01	12

1392, Avenue de la gare Mascouche (QC) Canada, J7K 2Z2

1-(888) 452-6382 (450) 477-3102 1-(450) 477-6664

www.ametasolution.com info@ametasolution.com



AMETA
SOLUTION.COM